MADE IN GERMANY

PALMERA FURNITURE



ROBUSTO

LAMINATE FLOORING

FSC www.fsc.org MIX Holz aus verantwortungsvollen Quellen FSC® C023682

BLAUER ENGEL DAS UMWELTZEICHEN

www.blauer-engel.de/uz176

FEUCHTESCHUTZ MOISTURE GUARD CORE

Profile optimised for 12mm 10mm panel thickness

PANEL 1375 x 188 x 12 mm | Box 5 panels | 1,293 m²

12 mm | 5G | clic | V4

33

ABRASION CLASS COMMERCIAL 33 / AC 5

Atlas Oak Coffee - D 3591 ER





Harbour Oak - D 3570 ER





Premium Oak Nature - D 4955 AF





Rip Oak White - D 3181 MX





Timeless Oak - D 3590 ER





Rip Oak - D 3075 MX





MADE IN GERMANY

ROBUSTO

LAMINATE FLOORING

TEST	CHARACTERISTICS	TEST METHOD
Formaldehyde emission	< 0.05 ppm	EN 717-1
Surface stain resistance	Grade 5, no visible changes to surface	EN 438-2.15
Lightfastness	≥ Level 6 Blue Wool Scale ≥ Level 4 Grey Scale	EN ISO 105-B02 EN 20 105-A02
Resistance to cigarette embers	Grade 4, no visible changes to surface	EN 438-2.18
Fire resistance	Ignites with difficulty, at least C_{fl}-s1	EN 13501-1
Height difference between connected elements	Average: ≤ 0.10 mm max: ≤ 0.15 mm	EN 13329
Edge straightness (bend)	≤ 0.3 mm/m	EN 13329
Openings between connected elements	Average: ≤ 0.15 mm max: ≤ 0.20 mm	EN 13329
Static indentation	< 0.01 mm - no visible changes, Impression in test with straight steel cylinder of 11.3 mm diameter	EN 433

THICKNESS	THERMAL CONDUCTIVITY (W/ (m x K))	OVERALL HEAT TRANSFER COEFFICIENT THERMAL RESISTANCE ((m² x K) / W)
12 mm	0.14	0.09

LENGTH	WIDTH	PANELS PER BOX	m²/BOX	BOXES PER PALLET	m² / PALLET
1375 mm	188 mm	5	1.293	56	72.380

GUARANTEE
25 Years (private) & 3 Years (commercial)

EN 14041

www.blauer-engel.de/uz176

PALMERA FURNITURE